Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.:	**2505038-001**
Date Test Report	**07-ott-25**
Acceptance:	**2505038**
Arrival date sample	**30-set-25**
Start date test	**30-set-25**
End date test	**07-ott-25**
References:	
Sampling Mode:	Sampling by Customer *

Customer Code 08796-1

Dear:
SILENT GLISS FABRICS & COMPONENTS GmbH
Rheinauenstrasse 8
79415 Bad Bellinen Germany
C.a.
Phone:

[C] Item:	**SOMNIA**
[C] Declared Composition:	**100% Polyester + Acrylic backing**
[C] End use:	**drapery**
[C] Typology:	**fabric**
Return:	**no requested**

Test Results

Test	Method	U.M.	Result
15246 FLAMMABILITY REQUIREMENTS FOR FABRICS CURTAINS, DRAPES AND WINDOW BLINDS (type B) **Start date test** 06/10/2025 **End date test** 07/10/2025 **Instrument:** Rhoburn Tester	**BS 5867-2:2008**		.
Pretreatment carried out			None
Test method used			Type B
Tested sample surface:			Face
Dimension of specimens:		mm	160x200
Type of gas used:			Propane
Type of ignition used:			Surface ignition
Time of application of flame:		s	15
Conditioning of sample			20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.			19°C - 48% r.h.
Number of tests specimens			6
TEST RESULT			SAMPLE MEETS THE BS 5867-2:2008 Type B REQUIREMENTS
Deviations from the method			None
Annex n.			1F

Details of the test results related to each specimen can be seen in the annex of this test report.

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.: **2505038-001**

Test	Method	U.M.	Result
* **25165 WASHING TREATMENTS**	**UNI EN ISO 10528:1997**		.
Start date test 30/09/2025 **End date test** 02/10/2025 **Instrument:** WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS Typology of washing machine used: Type A Programme of washing: 3N - normal agitation Test Temperature: 30°C Drying procedure: type C - Flat dry Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 12 THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of FLAMMABILITY REQUIREMENTS FOR FABRICS CURTAINS, DRAPES AND WINDOW BLINDS (type B).			
15246 FLAMMABILITY REQUIREMENTS FOR FABRICS CURTAINS, DRAPES AND WINDOW BLINDS (type B)	**BS 5867-2:2008**		.
Start date test 06/10/2025 **End date test** 07/10/2025 **Instrument:** Rhoburn Tester			
Pretreatment carried out			N. 12 washing at 30°C
Test method used			Type B
Tested sample surface:			Face
Dimension of specimens:		mm	160x200
Type of gas used:			Propane
Type of ignition used:			Surface ignition
Time of application of flame:		s	15
Conditioning of sample			20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.			19°C - 48% r.h
Number of tests specimens			6
TEST RESULT			SAMPLE MEETS THE BS 5867-2:2008 Type B REQUIREMENTS
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 331211
P. IVA - C.F. 03900470133
mailbox@textilecomo.com
www.textilecomo.com

00041

Test Report No.: **2505038-001**

Test	Method	U.M.	Result

The Laboratory Manager
Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.